

INERTOL

**Waterproofing and Anticorrosive Compound
for Concrete and Steel in
Waterworks, Hydraulic Structures, Sewage Disposal
Plants, Industrial Establishments.**

DIRECTIONS

INERTOL comes ready for use and is applied cold, preferably with long-handled, wide brush. It is also suitable for dip or spray. The surfaces to be coated must be clean and dry, especially free from oily substances. No priming is needed.

Two coats are necessary, the first of which must be thoroughly dry before the second is applied. Drying time will range from eight hours to several days according to temperature and weather conditions. Proper ventilation of confined places is essential, both to accelerate the drying and to avoid annoyance by vapors. Installation of small coke stoves is recommended inside of closed steel or concrete water tanks. There is no fire danger connected with their use. The treatment is perfect when the entire surface has become glossy black. If dull spots are visible after second coat, retouching of these spots is necessary.

INERTOL should be stored in tightly closed drums to avoid evaporation. Thickened material can be restored to normalcy by the addition of **DILUTING INERTOL** only, of which not more than 10% should be added under stirring. During the cold season, the drums require storing in warm premises for several days prior to use. **INERTOL** will not deteriorate.

Ask for Special Directions regarding the covering of **INERTOL**-treated surfaces with bright paints or cement mortar. Also concerning the use of **INERTOL PLASTIC** in expansion joints, large cracks, etc.

INERTOL-stains on skin or clothes can be removed with Gasoline or Benzol. Workmen should wear gloves and be careful of annoying vapors inside of tanks and other confined places.

APPLICATION TO CONCRETE AND MASONRY

After removal of dust and loose particles, brush **INERTOL** over dry surface in two consecutive coats, thinly and evenly. Do not spread second coat until the first one has become thoroughly hard.

APPLICATION TO IRON AND STEEL

Surface must be carefully derusted, dry and free from scale or grease. **INERTOL** can be brushed over an old coat of paint if same still adheres closely. Do not apply second coat as long as first one feels still tacky.

Concerning particular problems inquire direct from

INERTOL COMPANY, INC.

253 Broadway

New York City